

## EGOLF AGREEMENT 014-2016

Subject of Agreement	<b>Pipe insulation products with inner diameters &gt; 22 mm</b>
Related test standard	EN 13823
Date of issue	2016
Reference original query	TC1 N418rev1
Previous publication number (if applicable)	ER 59rev2
Keywords (max. 20)	pipe insulation, inner diameter, wall thickness

### Agreement

If the inner diameter of 22 mm is not producible there are two cases to be differentiated:

- 1) If an inner diameter less than 22 mm is producible, test the largest diameter near to 22 mm.

If only larger inner diameters are producible, test every wall thickness with its minimum and maximum inner diameter (1 single test in each case) and repeat twice the most critical case of each wall thickness for the classification.